

Asahi

#500


T/C bias tape

T/C バイアステープ

T/C bias tape


T/C バイアステープ
[#500]

Quality Sample



※ Will be discontinued due to limited stock.
※ 在庫限りで販売終了となります

Color Samples



Polyester 65%
 Cotton 35%
 ポリエステル 65%
 綿 35%


Fabric width 120cm
 生地巾 120cm



Washing cautions 洗濯上の注意

- Wash well with water. Hang out to dry immediately.
- Do not leave wrung or soaked in water for a long time.
- Do not use detergents with bleaching agents as they may cause the material to discolor. A neutral detergent is most suitable.
- 水洗いは充分にしてください。水洗いのあとは、早く干してください。
- 絞ったままや、水につけたままでの長時間にわたる放置は、さけてください。
- 漂白剤入りの洗剤をご使用になりますと、変色することがありますので、ご使用にならないでください。中性洗剤が最適です。

Care symbols 取扱い絵表示



Ironing caution アイロンがけの注意

- Dry completely before ironing. Ironing partially dry material may cause the color to fade.
- なま乾きのままでアイロンをかけると、色落ちすることがありますのでよく乾かしてからアイロンをかけてください。

Color list カラー一覧		Colorfastness 染色堅牢度	
501 V-17 V-105		Light 耐光堅牢度	Class 3 3級
503 V-18 V-109			
507 V-19 V-112		Dry rubbing 乾摩擦堅牢度	Class 4~5 4~5級
509 V-36 V-113			
517 V-37 V-114			
518 V-44		Wet rubbing 湿摩擦堅牢度	Class 4 4級
522 V-46			
527 V-50		Water 水堅牢度	Class 4~5 4~5級
534 V-101			
551 V-102			
561 V-103			
502 542 V-13 V-45 V-108 V-123		Light 耐光堅牢度	Class 3~4 3~4級
504 543 V-14 V-52 V-110 V-124			
508 544 V-16 V-54 V-111		Dry rubbing 乾摩擦堅牢度	Class 4 4級
510 548 V-22 V-60 V-115			
513 554 V-23 V-64 V-116			
519 558 V-28 V-65 V-117		Wet rubbing 湿摩擦堅牢度	Class 3 3級
532 559 V-30 V-70 V-118			
535 V-1 V-33 V-76 V-119		Water 水堅牢度	Class 4 4級
536 V-5 V-40 V-104 V-120			
538 V-8 V-41 V-106 V-121			
540 V-12 V-42 V-107 V-122			
505 530 V-10 V-51 V-68		Light 耐光堅牢度	Class 4 4級
506 531 V-11 V-53 V-71			
515 545 V-21 V-55 V-72		Dry rubbing 乾摩擦堅牢度	Class 3 3級
516 553 V-24 V-56 V-73			
521 555 V-25 V-57 V-74			
523 556 V-26 V-58 V-75		Wet rubbing 湿摩擦堅牢度	Class 3 3級
524 560 V-31 V-59 V-77			
525 V-2 V-34 V-61 V-78		Water 水堅牢度	Class 3~4 3~4級
526 V-3 V-35 V-62			
528 V-4 V-38 V-66			
529 V-9 V-43 V-67			